

# TECHNICAL DATA SHEET

SIMPSON COATINGS GROUP, INC.  
111 SOUTH MAPLE AVE.  
SOUTH SAN FRANCISCO, CA. 94080

1-800-877-5997

DATE: 5/23/05

## **IDENTIFICATION**

**Product:** Non Stearate 550 Clear Sanding Sealer

**Product Code:** 102 - 440

**Type of Material:** Nitrocellulose

**Solvents:** Acetone, Aliphatic Hydrocarbons, Alcohols, Toluene, Xylene, Petroleum Distillates

**Product Description:** A Clear Sanding Sealer, which is to be finished coated with Simpson Coatings Clear or Pigmented CAB Acrylic Lacquers, PreCatalyzed Lacquers, Conversions Varnishes and 2 part Urethane Finishes.

**Where to Use:** Product is designed to be used on interior wood substrates.

## **PHYSICAL CONSTANTS**

**Viscosity:** 23 - 29 #2 Zahn @ 77° F

**Weight Per Gallon:** 7.1 - 7.7

**Non-Volatile Material:** 23.2 - 25.3% By Wt.

16.4 - 18.3% By Vol.

**Gloss @ 60 Degrees:** 40 - 60

**Coatings V.O.C.:** Does not exceed 550 grams per liter.

## **APPLICATION INFORMATION**

**Method of Application:** Professional, HVLP, Airless/Conventional Spray Technology.

**Application Viscosity:** As Packaged.

**Required Reducer & Ratio:** DO NOT THIN THIS PRODUCT. This product is ready to apply as packaged. Thinning this product can adversely affect the film building properties, dry / cure times, and volatile organic compound (V.O.C.) emissions.

**Clean Up:** Use Simpson Coatings #304-013 Acetone for cleaning purposes only!

**Wet Film Thickness:** 3.2 - 5.0 mils

**Dry Film Thickness:** 0.5 - 0.8 mils

**Spread Rate:** Estimated practical coverage is 250 - 275 sq. ft. per gallon @ recommended wet mil thickness, depending on application technique and the porosity of the substrate.

**Substrate:** Interior Wood

**Surface Preparation:** All surfaces must be clean, dry and free of dust, dirt, oil, grease, wax or any contamination that would adversely affect the adhesion or performance of this coating.

**Application Direction:** Estimation of practical coverage of this product can be variable, and is completely dependent on the application technique i.e.; (determine the amount of wet film thickness to achieve the dry film thickness) and the porosity of the substrate. Drying times may be adversely affected by extreme high/low Temperature and Humidity Variances. Apply when the product, air, and surface temperatures are between 50 ° and 85 ° Fahrenheit, the relative humidity is no greater than 85% Max, and the surface is at least 5° Fahrenheit, above the dew point.

**Air Dry Schedule:** Tack Free: 10 - 15 Min., Handle: 15 - 30 Min., Sand/Recoat: 30 - 60 Min., Dry Hard/Full Cure: 60 - 90 Min.

## **TESTING DATA**

**Interior/Exterior Durability:** N/A

**Salt Spray/Humidity Resistance:** N/A

**WARNING:** This product contains chemicals known to the State of California to cause cancer and birth defects or other reproductive harm.

*Recommendations are based on tests and information to be reliable. However, since we have no control over the conditions under which our products are stored, used, or handled, there are no warranties expressed or implied that the products are fit for a particular purpose.*

### **LIMITED WARRANTY**

The statements made on this bulletin, product label, or by any of our agents concerning these materials are given for information only. They are believed to be true and accurate and are intended to provide a guide to approved construction practices and materials. As workmanship, weather, construction equipment, quality of other materials and other variables affecting results are all beyond our control. The Simpson Coatings Group, does not make nor does it authorize any agent or representative to make any warranty of MERCHANTABILITY OR Fitness for any purpose or any other warranty, guarantee or representation, express or implied, concerning this material except that it conforms to Simpson Coatings quality control standards. Any liability whatsoever of Simpson Coatings Group to the buyer or user of this product is limited to the purchaser cost of the product itself.